



**TECHNICAL DATASHEET**  
**CARAPACE<sup>®</sup>**  
**EMP110 W- LED**  
**Aqueous Developable**  
**PHOTOIMAGEABLE SOLDERMASK**  
**for LED applications**

**PRODUCT DESCRIPTION**

**Carapace<sup>®</sup> EMP110** has been used in the high volume production of PCBs since 1987. **EMP110 W-LED** has been formulated specifically to have a strong white colour and very low colour change during high temperature processing.

- **Fast processing times allowing High throughput and productivity.**
- **Contains no halogenated flame retardants.**
- **EMP110 W-LED is RohS compliant.**

**Carapace<sup>®</sup> EMP110 W-LED** is a contact exposure, aqueous developing, liquid photoimageable soldermask, using two-component epoxy technology.

**CARAPACE<sup>®</sup> EMP110 W-LED**

All **Carapace<sup>®</sup>** pastes are coded as EMP110 followed by a 4-figure number and letters. The 4-figure number and letters denote the colour, finish.

E.g. **EMP110/4889 WG - LED**

Product Family: **EMP110**  
Product reference: **4889**  
Colour & Finish: **W G**

**Carapace<sup>®</sup> EMP110 W-LED** is only available in **WHITE GLOSS** for screen-printing

**HARDENER:**

EMP110 W - LED is specifically designed for use with EMP110 PtB (H-4890).

[www.electrapolymers.com](http://www.electrapolymers.com)

EMP110 W-LED



**Board surface preparation:**

Copper surfaces should be mechanically or chemically cleaned to give a 60s waterbreak-free surface. Recommended mechanical methods are pumice, aluminium oxide or 320 grit brush.

All boards **must** be completely dry before coating.

**Mixing:**

Carapace<sup>®</sup> is supplied pre-weighed in 1kg or 3kg packs.

The resist should be mixed in the ratio 100 parts paste (pt A) to 19 parts hardener by weight. Stir well to ensure complete mixing.

Incomplete mixing can cause poor developing, stickiness during exposure and impaired final properties.

**Viscosity reduction:**

EMP110 W-LED is supplied screen ready. If viscosity adjustment is required prior to, or during printing, then this may be achieved using **Electra-reducer ER1**. No more than 5% reducer should be added or deterioration of the printing and drying properties may occur, resulting in thin deposits on track edges and/or prolonged drying times.

**Process settings:**

Mesh count: 37-55T polyester.  
Squeegee: 60-70 Shore.

20µm dry thickness should be aimed for; this is typically achieved using a 43T.

The board outline image may be made on the screen using conventional stencil material or masking tape and screen filler. To prevent a build up of ink on the reverse of the screen that may block holes, it is advisable to shift alternate boards along the x- or y-axis before printing. Alternatively, a rudimentary stencil, such as an expanded drill mask, can be used on the screen to prevent ink going into the holes.

**Do not** utilise the vacuum bed, as this will suck an exaggerated amount of ink into the holes.

**Tack-dry:**

The aim of the tack-drying stage is to solely remove the solvents. It is important for the drying chamber (static or conveyerised) to have good air circulation with air supply and extraction facilities.

**Convection dry**

Recommended drying settings and hold times will vary with hardener selection, see below.

Hardener	Recommended/Max temperature	Recommended/Max time (mins)	Max hold-time after optimum tack-dry
H-4890	75 °C (167°F)	30 – 45	24 hours



### **Exposure**

Spectral output: 310-420 nm. Optimum wavelength is approx. 365-385nm.

Step wedge: 7-10 clear (Stouffer 21 step).

Determination of the correct exposure should be carried out after setting the developing speed since this will affect the step wedge reading obtained.

Step wedge checks should be carried out on brushed copper with the step wedge under the phototool. Energy level should be measured through the artwork and mylar/glass. It is important to recognise that the energy level should only be used as a guide for setting the correct exposure; step wedges should be used for determining the actual exposure setting.

Separate exposure tests should be carried out for each different colour, as variations in lamp emissions can cause differences in exposure speed. After determining the correct setting, energy level can be monitored as a means to check for any changes in lamp output.

### **Developing**

Developer: 1% soln sodium or potassium carbonate.

Spray pressure: 2.5 – 3.0 kgcm<sup>-2</sup>, 35 - 45 psi.

Spray time: 45 - 60s in carbonate chamber(s) (dependent on quantity of ink in holes).

Temperature: 31 - 33°C

Boards should be well rinsed with fresh water and fully dried after developing.

Do not final cure boards when wet.

The optimum developing speed is set when an unexposed board develops off completely, 25- 50% of the way through the machine. This speed should be ascertained by preliminary tests prior to making exposure tests.

**Developing speed and break-point settings will be determined by the amount of ink deposited in the holes during coating.**

**Final Cure**                      Convection oven:              60 mins at 150°C                      **Time at board temperature**

### **UV bumping**

It is not recommended to UV bump Carapace<sup>®</sup> EMP110 W-LED

### **Safelight**

It is not normally necessary to print Carapace<sup>®</sup> EMP110 W-LED under safelight conditions, although it may be advisable if there are long delays before drying. Between drying/exposing and exposing/developing, boards should be kept in yellow light. Boards should, in any case, be kept out of direct sunlight until completely processed.

### **Notation/marketing inks**

Thermal curing notation inks are suitable for use with Carapace<sup>®</sup> EMP110 W-LED. Thermal curing inks may be applied before or after final cure.

[www.electrapolymers.com](http://www.electrapolymers.com)

EMP110 W-LED



### Stripping

After developing, any reject boards may be stripped of soldermask using a 5% NaOH solution at 40-50°C

After curing, soldermask can be stripped using a proprietary soldermask stripper such as **ES108H**.

### Cleaning

Equipment should be cleaned of residual soldermask using **SW100** or **Dowanol PMA**.

### Shelf-life

Minimum 6 months from date of manufacture when stored in cool, dry, recommended conditions.  
Storage should be between 10 and 25°C and must be away from sources of heat and direct sunlight.

### Final Properties

TEST	METHOD	RESULT	CLASSIFICATION
<b>Hardness (pencil)</b>	SM-840C	4H	Pass, class H
<b>Adhesion</b>	SM-840C	Copper: 0% removal Base laminate: 0% removal SnPb: <10% removal	Pass, class H
<b><u>Chemical resistance</u></b> Isopropanol (min.120s) Isopropanol/H <sub>2</sub> O (75/25) D-Limonene 10% Alkaline detergent Monoethanolamine Methylene chloride Deionised water	SM-840C  Room temp. 120s 46 (± 2)°C 15 min Room temp. 120s 57 (± 2)°C 120s 57 (± 2)°C 120s Room temp. 60s 60 (± 2)°C 5 min	No surface roughness No blisters No delamination No swelling No colour change No cracking	Pass, class H
<b>Hydrolytic stability</b>	SM-840C	No evidence of reversion	Pass, class H
<b>Insulation resistance</b>	SM-840C	Before solder 2 x 10 <sup>13</sup> Ω After solder 2 x 10 <sup>12</sup> Ω	Pass, class H
<b>Moisture &amp; insulation</b>	SM-840C	No blistering, separation, degradation. Initial 2 x 10 <sup>13</sup> Ω After 2 x 10 <sup>12</sup> Ω	Pass, class H
<b>Wave-solder resistance</b> 10 (± 1)s at 260 (± 5)°C	SM-840C	No loss of adhesion or solder pick-up.	Pass, class H
<b>Thermal shock</b>	SM840 C	No cracks, delamination, crazing or blistering	Pass , class H



TEST	METHOD	RESULT	CLASSIFICATION
Dielectric strength	SM840 C	1900 V/mil	Pass , class H
Dielectric Constant		4.5 (1MHz)	

Other

UL File E95722

94 V-0

For further information, contact:

Electra  
 Roughway Mill  
 Dunk's Green  
 Tonbridge  
 Kent TN11 9SG  
 ENGLAND

Tel: +44 (0)1732 811 118  
[info@electrapolymers.com](mailto:info@electrapolymers.com)

Or visit our Website for details of local offices and Distributors

[www.electrapolymers.com](http://www.electrapolymers.com)

The Laboratories at Electra Polymers & Chemicals Ltd. have taken all reasonable steps to ensure that the information set out above is accurate within the scope and limitations of our existing knowledge and experience. Since, however, we cannot anticipate or control the many interrelated conditions under which our products are used, all our products are offered for sale and trial on the basis that clients will satisfy themselves by tests or otherwise on these products, that they are fit, suitable and safe for the purpose for which they are required, within the parameters and conditions in which they will be used. In cases where our products are found to be defective in material and workmanship, our liability is limited to the purchase price of the products found to be defective. THIS WARRANTY IS TO THE EXCLUSION OF ALL OTHER WARRANTIES OR GUARANTEES, EXPRESS OR IMPLIED, AS TO MERCHANTABILITY, FITNESS FOR ANY PARTICULAR PURPOSE, DESCRIPTION PRODUCTIVENESS OR ANY OTHER MATTER. None of the above information may be construed as a recommendation that our products be used in violation of any patent rights. We accept your orders at our shipping points only on the basis of the above understanding, set out in our detailed "Standard Terms + Conditions of sale". E & OE.

[www.electrapolymers.com](http://www.electrapolymers.com)

EMP110 W-LED